


POLIURETANO / POLYURETHANE

MARRONE - BROWN




Sezione Section	Dimensioni Sizes
A	13x15
B	17x20
C	22x25

Durezza - Hardness	80Sh		
Temperatura ideale Saldatura / Advised Welding Temperature	240°C		
Temperatura Esercizio / Temperature Range	-30°C/+60°C		
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51		
Pretensionamento=Sviluppo / Tensioning=Length	-5%		
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
11	110	0,16	30
19	130	0,26	30
32	190	0,47	30

POLIURETANO / POLYURETHANE

BIANCO - WHITE



Sezione Section	Dimensioni Sizes
A	13x15
B	17x20
C	22x25

Durezza - Hardness	85Sh		
Temperatura ideale Saldatura / Advised Welding Temperature	240°C		
Temperatura Esercizio / Temperature Range	-30°C/+75°C		
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51		
Pretensionamento=Sviluppo / Tensioning=Length	-3%		
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
28	160	0,16	30
40	180	0,26	30
64	210	0,47	30

POLIURETANO / POLYURETHANE

VERDE - GREEN




Sezione Section	Dimensioni Sizes
A	13x15
B	17x20
C	22x25

Durezza - Hardness	85Sh		
Temperatura ideale Saldatura / Advised Welding Temperature	240°C		
Temperatura Esercizio / Temperature Range	-30°C/+75°C		
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51		
Pretensionamento=Sviluppo / Tensioning=Length	-3%		
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
28	160	0,16	30
40	180	0,26	30
64	210	0,47	30

POLIURETANO / POLYURETHANE

TRASPARENTE - TRANSPARENT




Sezione Section	Dimensioni Sizes
A	13x15
B	17x20
C	22x25

Durezza - Hardness	85Sh		
Temperatura ideale Saldatura / Advised Welding Temperature	240°C		
Temperatura Esercizio / Temperature Range	-30°C/+75°C		
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51		
Pretensionamento=Sviluppo / Tensioning=Length	-3%		
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
28	160	0,16	30
40	180	0,26	30
64	210	0,47	30

RINFORZATA CRESTATA CC / RIDGED CC REINFORCED

POLIURETANO / POLYURETHANE

AZZURRA - BLUE




Sezione Section	Dimensioni Sizes
A	13x15
B	17x20
C	22x25

Durezza - Hardness	80Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+60°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Length	-1,5%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
19	110	0,16	30	
31	130	0,26	30	
53	190	0,44	30	

POLIURETANO / POLYURETHANE

BIANCO - WHITE



Sezione Section	Dimensioni Sizes
A	13x15
B	17x20
C	22x25

Durezza - Hardness	85Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+75°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Length	-1,5%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
33	160	0,16	30	
48	180	0,26	30	
77	210	0,44	30	

POLIURETANO / POLYURETHANE

VERDE - GREEN




Sezione Section	Dimensioni Sizes
A	13x15
B	17x20
C	22x25

Durezza - Hardness	85Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+75°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Length	-1,5%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
33	160	0,16	30	
48	180	0,26	30	
77	210	0,44	30	

POLIURETANO / POLYURETHANE

TRASPARENTE - TRANSPARENT



Sezione Section	Dimensioni Sizes
A	13x15
B	17x20
C	22x25

Durezza - Hardness	85Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+75°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Length	-1,5%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
33	160	0,16	30	
48	180	0,26	30	
77	210	0,44	30	