


POLIURETANO / POLYURETHANE

MARRONE - BROWN




Sezione Section	Dimensioni Sizes
A	13x13
B	17x16
C	22x19

Durezza - Hardness	80Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+60°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Length	-5%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
8	65	0,15	30	
14	90	0,23	30	
23	115	0,34	30	

POLIURETANO / POLYURETHANE

BIANCO - WHITE




Sezione Section	Dimensioni Sizes
A	13x13
B	17x16
C	22x19

Durezza - Hardness	85Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+75°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Length	-3%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
18	70	0,15	30	
29	110	0,23	30	
48	135	0,34	30	

POLIURETANO / POLYURETHANE

VERDE - GREEN




Sezione Section	Dimensioni Sizes
A	13x13
B	17x16
C	22x19

Durezza - Hardness	85Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+75°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Length	-3%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
18	70	0,15	30	
29	110	0,23	30	
48	135	0,34	30	

POLIURETANO / POLYURETHANE

TRASPARENTE - TRANSPARENT




Sezione Section	Dimensioni Sizes
A	13x13
B	17x16
C	22x19

Durezza - Hardness	85Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+75°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Length	-3%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
18	70	0,15	30	
29	110	0,23	30	
48	135	0,34	30	

POLIURETANO / POLYURETHANE RS

ROSSO - RED




Sezione Section	Dimensioni Sizes
A	13x13
B	17x16
C	22x19

Durezza - Hardness	85Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+75°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Length	-3%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
18	70	0,15	30	
29	110	0,23	30	
48	135	0,34	30	

RINFORZATA RND PU / PU HONEYCOMB BACKING REINFORCED

POLIURETANO / POLYURETHANE

AZZURRA - BLUE




Sezione Section	Dimensioni Sizes
A	13x13
B	17x16
C	22x19

Durezza - Hardness	80Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+60°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Length	-1,5%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
14	60	0,15	30	
23	85	0,23	30	
38	110	0,34	30	

POLIURETANO / POLYURETHANE

BIANCO - WHITE




Sezione Section	Dimensioni Sizes
A	13x13
B	17x16
C	22x19

Durezza - Hardness	85Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+75°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Length	-1,5%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
22	70	0,15	30	
35	110	0,23	30	
58	135	0,34	30	

POLIURETANO / POLYURETHANE

VERDE - GREEN




Sezione Section	Dimensioni Sizes
A	13x13
B	17x16
C	22x19

Durezza - Hardness	85Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+75°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Length	-1,5%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
22	70	0,15	30	
35	110	0,23	30	
58	135	0,34	30	

POLIURETANO / POLYURETHANE

TRASPARENTE - TRANSPARENT



Sezione Section	Dimensioni Sizes
A	13x13
B	17x16
C	22x19

Durezza - Hardness	85Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+75°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Length	-1,5%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
22	70	0,15	30	
35	110	0,23	30	
58	135	0,34	30	