


POLIURETANO / POLYURETHANE

MARRONE - BROWN




Sezione Section	Dimensioni Sizes
A	13x13
B	17x16
C	22x19

Durezza - Hardness		80Sh	
Temperatura ideale Saldatura / Advised Welding Temperature		240°C	
Temperatura Esercizio / Temperature Range		-30°C/+60°C	
Coefficiente d'attrito / Friction Coefficient		Acciaio / Steel - 0,51	
Pretensionamento=Sviluppo / Tensioning=Length		-5%	
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
8	65	0,15	30
14	90	0,23	30
23	115	0,34	30

POLIURETANO / POLYURETHANE

BIANCO - WHITE




Sezione Section	Dimensioni Sizes
A	13x13
B	17x16
C	22x19

Durezza - Hardness		85Sh	
Temperatura ideale Saldatura / Advised Welding Temperature		240°C	
Temperatura Esercizio / Temperature Range		-30°C/+75°C	
Coefficiente d'attrito / Friction Coefficient		Acciaio / Steel - 0,51	
Pretensionamento=Sviluppo / Tensioning=Length		-3%	
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
18	70	0,15	30
29	110	0,23	30
48	135	0,34	30

POLIURETANO / POLYURETHANE

VERDE - GREEN




Sezione Section	Dimensioni Sizes
A	13x13
B	17x16
C	22x19

Durezza - Hardness			85Sh
Temperatura ideale Saldatura / Advised Welding Temperature			240°C
Temperatura Esercizio / Temperature Range			-30°C/+75°C
Coefficiente d'attrito / Friction Coefficient			Acciaio / Steel - 0,51
Pretensionamento=Sviluppo / Tensioning=Length			-3%
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
18	70	0,15	30
29	110	0,23	30
48	135	0,34	30

POLIURETANO / POLYURETHANE

TRASPARENTE - TRANSPARENT




Sezione Section	Dimensioni Sizes
A	13x13
B	17x16
C	22x19

Durezza - Hardness			85Sh
Temperatura ideale Saldatura / Advised Welding Temperature			240°C
Temperatura Esercizio / Temperature Range			-30°C/+75°C
Coefficiente d'attrito / Friction Coefficient			Acciaio / Steel - 0,51
Pretensionamento=Sviluppo / Tensioning=Length			-3%
Carico max / Max Load	Diam. Pulegge / Pulley Diam.	Peso / Weight	Lung. Rotolo / Roll length
Kg.	mm	Kg/mt	mt
18	70	0,15	30
29	110	0,23	30
48	135	0,34	30

POLIURETANO / POLYURETHANE RS





ROSSO - RED



Sezione Section	Dimensioni Sizes
A	13x13
B	17x16
C	22x19

Durezza - Hardness			85Sh
Temperatura ideale Saldatura / Advised Welding Temperature			240°C
Temperatura Esercizio / Temperature Range			-30°C/+75°C
Coefficiente d'attrito / Friction Coefficient			Acciaio / Steel - 0,51
Pretensionamento=Sviluppo / Tensioning=Length			-3%
Carico max / Max Load	Diam. Pulegge / Pulley Diam.	Peso / Weight	Lung. Rotolo / Roll length
Kg.	mm	Kg/mt	mt
18	70	0,15	30
29	110	0,23	30
48	135	0,34	30

RINFORZATA RND PARA / PVC CON ELASTOMERO RED HONEYCOMB BACKING REINFORCED PARA / PVC WITH ELASTOMER

POLIURETANO / POLYURETHANE	AZZURRA - BLUE		Durezza - Hardness		80Sh	
			Temperatura ideale Saldatura / Advised Welding Temperature		240°C	
			Temperatura Esercizio / Temperature Range		-30°C/+60°C	
			Coefficiente d'attrito / Friction Coefficient		Acciaio / Steel - 0,51	
			Pretensionamento=Sviluppo / Tensioning=Length		-1,5%	
	Sezione Section	Dimensioni Sizes	Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
	A	13x13	14	60	0,10	30
	B	17x16	23	85	0,18	30
	C	22x19	38	110	0,29	30
POLIURETANO / POLYURETHANE	BIANCO - WHITE		Durezza - Hardness		85Sh	
			Temperatura ideale Saldatura / Advised Welding Temperature		240°C	
			Temperatura Esercizio / Temperature Range		-30°C/+75°C	
			Coefficiente d'attrito / Friction Coefficient		Acciaio / Steel - 0,51	
			Pretensionamento=Sviluppo / Tensioning=Length		-1,5%	
	Sezione Section	Dimensioni Sizes	Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
	A	13x13	22	70	0,10	30
	B	17x16	35	110	0,18	30
	C	22x19	58	135	0,29	30
POLIURETANO / POLYURETHANE	VERDE - GREEN		Durezza - Hardness		85Sh	
			Temperatura ideale Saldatura / Advised Welding Temperature		240°C	
			Temperatura Esercizio / Temperature Range		-30°C/+75°C	
			Coefficiente d'attrito / Friction Coefficient		Acciaio / Steel - 0,51	
			Pretensionamento=Sviluppo / Tensioning=Length		-1,5%	
	Sezione Section	Dimensioni Sizes	Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
	A	13x13	22	70	0,10	30
	B	17x16	35	110	0,18	30
	C	22x19	58	135	0,29	30
POLIURETANO / POLYURETHANE	TRASPARENTE - TRANSPARENT		Durezza - Hardness		85Sh	
			Temperatura ideale Saldatura / Advised Welding Temperature		240°C	
			Temperatura Esercizio / Temperature Range		-30°C/+75°C	
			Coefficiente d'attrito / Friction Coefficient		Acciaio / Steel - 0,51	
			Pretensionamento=Sviluppo / Tensioning=Length		-1,5%	
	Sezione Section	Dimensioni Sizes	Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
	A	13x13	22	70	0,10	30
	B	17x16	35	110	0,18	30
	C	22x19	58	135	0,29	30