


AZZURRA - BLUE




Diam. Disponibili / Avail. diameters
mm

6
7
8
9
10
12
15
18

Durezza - Hardness	80Sh
Temperatura ideale Saldatura / Advised Welding Temperature	240°C
Temperatura Esercizio / Temperature Range	-30°C/+65°C
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51
Pretensionamento=Sviluppo / Tensioning=Length	-1,5%

Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
6,3	43	0,034	50
8,2	51	0,047	50
10,5	58	0,06	50
14	63	0,077	50
16	70	0,095	50
21	80	0,14	50
32	106	0,21	50
43	126	0,31	50

BIANCO - WHITE




Diam. Disponibili / Avail. diameters
mm

6
7
8
9
10
12
15
18

Durezza - Hardness	85Sh
Temperatura ideale Saldatura / Advised Welding Temperature	240°C
Temperatura Esercizio / Temperature Range	-30°C/+65°C
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51
Pretensionamento=Sviluppo / Tensioning=Length	-1,5%

Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
10	58	0,034	50
16	70	0,047	50
18	80	0,06	50
23	95	0,082	50
28	110	0,095	50
37	125	0,13	50
50	138	0,21	50
63	153	0,32	50

VERDE - GREEN



Diam. Disponibili / Avail. diameters
mm


6
7
8
9
10
12
15
18

Durezza - Hardness	87Sh
Temperatura ideale Saldatura / Advised Welding Temperature	240°C
Temperatura Esercizio / Temperature Range	-30°C/+65°C
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,38
Pretensionamento=Sviluppo / Tensioning=Length	-1,5%

Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
12	60	0,034	50
19	72	0,046	50
22	82	0,06	50
28	98	0,082	50
33	118	0,095	50
40	135	0,13	50
56	145	0,21	50
70	160	0,32	50

RINFORZATA / REINFORCED

TRASPARENTE - TRANSPARENT



Diam. Disponibili / Avail. diameters
mm


Diam. Disponibili / Avail. diameters mm	Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
6	10	58	0,034	50
7	16	70	0,046	50
8	18	80	0,06	50
9	23	93	0,082	50
10	28	110	0,095	50
12	37	125	0,13	50
15	50	138	0,21	50
18	63	153	0,32	50

Durezza - Hardness	85Sh
Temperatura ideale Saldatura / Advised Welding Temperature	240°C
Temperatura Esercizio / Temperature Range	-30°C/+65°C
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51
Pretensionamento=Sviluppo / Tensioning=Length	-1,5%

POLIURETANO / POLYURETHANE

RUGOSA RINFORZATA / ROUGH REINFORCED

VERDE - GREEN



Diam. Disponibili / Avail. diameters
mm

Diam. Disponibili / Avail. diameters mm	Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt
6	12	60	0,034	50
7	19	72	0,046	50
8	22	82	0,06	50
10	33	118	0,095	50
12	40	135	0,13	50
15	56	145	0,21	50
18	70	160	0,32	50
20	80	180	0,40	50

Durezza - Hardness	87Sh
Temperatura ideale Saldatura / Advised Welding Temperature	240°C
Temperatura Esercizio / Temperature Range	-30°C/+65°C
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,38
Pretensionamento=Sviluppo / Tensioning=Length	-1,5%

POLIURETANO / POLYURETHANE