



MARRONE - BROWN



Sezione Section	Dimensioni Sizes
A	13x15
B	17x20
C	22x25

Durezza - Hardness	80Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+60°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Development	-5%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
11	110	0,14	30	
19	130	0,24	30	
32	190	0,45	30	


BIANCO - WHITE



Sezione Section	Dimensioni Sizes
A	13x15
B	17x20
C	22x25

Durezza - Hardness	85Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+75°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Development	-3%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
26	160	0,14	30	
37	180	0,24	30	
60	210	0,45	30	

VERDE - GREEN



Sezione Section	Dimensioni Sizes
A	13x15
B	17x20
C	22x25

Durezza - Hardness	85Sh			
Temperatura ideale Saldatura / Advised Welding Temperature	240°C			
Temperatura Esercizio / Temperature Range	-30°C/+75°C			
Coefficiente d'attrito / Friction Coefficient	Acciaio / Steel - 0,51			
Pretensionamento=Sviluppo / Tensioning=Development	-3%			
Carico max / Max Load Kg.	Diam. Pulegge / Pulley Diam. mm	Peso / Weight Kg/mt	Lung. Rotolo / Roll length mt	
26	160	0,14	30	
37	180	0,24	30	
60	210	0,45	30	